

IN THE CLAIMS

1. (Currently Amended) A method of manufacturing a silicon microphone ~~including~~ comprising the steps of:

providing a first wafer ~~including~~ having a layer of heavily doped silicon, a layer of silicon and an intermediate layer of oxide between the two silicon layers, and ~~having~~ a first major surface on ~~one surface of~~ the layer of heavily doped silicon and a second major surface on the layer of silicon,

providing a second wafer of silicon having a first major surface and a second major surface,

forming a layer of oxide on at least the first major surface of the first wafer,

forming a layer of oxide on at least the first major surface of the second wafer,

etching a cavity ~~through the oxide layer on the first major surface of the first wafer and into the layer of heavily doped silicon~~ and through the layer of oxide on the first major surface of the first wafer, to form a diaphragm,

bonding the first major surface of the first wafer to the first major surface of the second wafer,

forming a metal layer on the second major surface of the second wafer,

patterning and etching acoustic holes in the metal and in the second major surface of the second wafer, and

forming at least one electrode on the heavily doped silicon of the first wafer and at least one electrode on the second wafer, ~~and~~

~~further including the step of etching the oxide layer of the first wafer from at least the back of a diaphragm during manufacturing of the silicon microphone.~~

2. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 1 further ~~including the step of thinning a portion of the second major surface of the first wafer to form a diaphragm for the silicon microphone.~~ comprising the

step of etching the intermediate layer of oxide of the first wafer at a back of the diaphragm.

3. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 2, wherein the step of etching ~~a portion of the second major surface of the first wafer~~ the cavity is performed before bonding the first major surface of the first wafer to the first major surface of the second wafer.

4. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 2, wherein the step of etching ~~a portion of the second major surface of the first wafer~~ the intermediate layer of oxide is performed after bonding the first major surface of the first wafer to the first major surface of the second wafer.

5. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 1 further ~~including~~ comprising the step of etching corrugations in the diaphragm ~~of the silicon microphone.~~

6. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the step of forming an oxide layer on at least ~~one~~ the first major surface of both the first wafer and the second wafers ~~includes~~ comprises forming an oxide layer on ~~both~~ each major surfaces of ~~both~~ each wafers.

7. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the oxide layers formed on the major faces of the wafers are grown on the major surfaces of the wafers.

8. (Cancelled)

9. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 2 wherein the oxide layer formed on the second major surface of the second wafer is removed before the first wafer is thinned.

10. (Cancelled)

11. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the step of forming a layer of metal on the second major surface of the second wafer is performed by sputtering metal onto the second major surface of the second wafer.
12. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 1 further ~~including~~ comprising the step of etching a portion of the second wafer from its second major surface to close to its first major surface, the portion being about the perimeter of the wafer.
13. (Original) A method of manufacturing a silicon microphone as claimed in claim 12 wherein the etching of the perimeter portion of the second wafer is performed when the acoustic holes are etched.
14. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein when the first wafer is thinned at its second major surface, the first wafer is thinned to the intermediate oxide layer.
15. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the step of forming electrodes on the heavily doped silicon layer of the first wafer and on the second wafer is performed by forming a metal electrode layer over the entire exposed surface of the heavily doped silicon layer of the first wafer and the exposed surface of the first major surface of the second wafer.
16. (Original) A method of manufacturing a silicon microphone as claimed in claim 15 wherein the metal electrode layer is etched to form the electrodes.
17. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the step of forming electrodes on the heavily doped silicon layer of the first wafer and on the second wafer is performed by sputtering metal and using a shadow mask to pattern the electrodes.

18. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein the layer of metal formed on the second major surface of the second wafer is an alloy or mixture of chromium and gold.
19. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein any suitable conductive metal is used for the electrode.
20. (Previously Presented) A method of manufacturing a silicon microphone as claimed in claim 1 wherein when the acoustic holes are patterned and etched into the metal layer formed on the second major surface of the second wafer, anchors are patterned and formed at the edges of the wafer in the metal layer formed on the second major surface of the second wafer.
21. (Original) A method of manufacturing a silicon microphone as claimed in claim 20 wherein one of the anchors may be used as an electrode.
22. (Original) A method of manufacturing a silicon microphone as claimed in claim 21, wherein the other anchors include both a portion of the second wafer and a cover portion of metal.
23. (Original) A method of manufacturing a silicon microphone as claimed in claim 22 wherein the cover metal portions are separated from metal surrounding the acoustic holes.
24. (Currently Amended) A method of manufacturing a silicon microphone as claimed in claim 23 wherein the separation step the cover metal portions are separated from the metal is performed by patterning and etching the separation when the acoustic holes are patterned and etched in the metal.
25. (Cancelled)